


ポリテックスロープ (3打)

側面写真



断面形状



呼称太さ (mm)	質量(kg/200m)					引張強さ (tonf)
	甘打	やや甘打	並打	やや硬打	硬打	
8	6.6	6.8	6.9	7.1	7.3	0.7
10	10.4	10.7	10.9	11.2	11.5	1.0
12	14.7	15.1	15.5	15.9	16.2	1.4
14	20.1	20.6	21.2	21.7	22.2	1.8
16	26.2	26.9	27.6	28.3	29.0	2.4
18	33.0	33.9	34.7	35.6	36.5	2.9
20	40.9	42.0	43.1	44.1	45.2	3.6
22	49.5	50.8	52.1	53.4	54.7	4.3
24	58.9	60.5	62.0	63.6	65.1	5.0
26	70.0	71.8	73.7	75.5	77.4	5.8
28	81.2	83.3	85.5	87.6	89.7	6.7
30	93.3	95.8	98.2	100.7	103.1	7.6
32	105.5	108.3	111.1	113.8	116.6	8.4
34	118.9	122.0	125.2	128.3	131.4	9.6
36	132.0	135.5	138.9	142.4	145.9	10.6
38	147.6	151.5	155.4	159.3	163.1	11.7
40	164.0	168.3	172.6	176.9	181.3	12.9
42	182.4	187.2	192.0	196.8	201.6	14.0
45	212.4	218.0	223.6	229.2	234.8	16.0
48	242.2	248.6	254.9	261.3	267.7	18.2
50	262.2	269.1	276.0	282.9	289.8	19.5